

School Bus Seating

Construction Properties		Standard	Remarks
Thickness		0.80mm	+/- 0.05mm
Width		66"	-0.5" / +1"
Weight		42oz	+/- 2oz per linear yard
Backing		Polyester	Jersey Knitted
Roll Size		40 yards	2" ID paper core
Formulation(1)		CPSIA Compliance	6P < 1,000PPM
Formulation(2)		Proposition 65	Lead content < 90PPM
Physical Properties		Standard	Remarks
Tensile Strength	MD	150 lbf	ASTM D5034
	CD	120 lbf	
Tear Strength	MD	40 lbf	ASTM D5587
	CD	35 lbf	
Adhesion Strength	MD	4 lbf	ASTM D751
	CD	4 lbf	
Abrasion		Wyzenbeek	100,000 cycles
		Martindale	50,000 cycles
Flex Resistance		Normal Temperature	50,000 times
Color Fastness to Crocking		Dry / Wet	Grade 4
Color Fastness to Artificial Light		Xenon Arc Lamp	Grade 5
Fire Resistance		FMVSS302	Pass
Cold Crack Resistance		ASTM D1790 at -20 $^{\circ}\mathrm{F}$	Pass
Anti-UV Resistance		650 hours	Pass
Mildew Resistance		ASTM G-21-90 / AATCC 147-2011	Pass